



(19) **United States**

(12) **Patent Application Publication**

Laven et al.

(10) **Pub. No.: US 2020/0227518 A1**

(43) **Pub. Date: Jul. 16, 2020**

(54) **SEMICONDUCTOR DEVICE WITH STRIPE-SHAPED CELL TRENCH STRUCTURES AND RECESSED CONTACTS AND METHOD OF MANUFACTURING THEREOF**

H01L 21/223 (2006.01)
H01L 21/311 (2006.01)
H01L 29/08 (2006.01)
H01L 29/10 (2006.01)
H01L 29/423 (2006.01)

(71) Applicant: **Infineon Technologies AG**, Neubiberg (DE)

(52) **U.S. Cl.**
CPC *H01L 29/06* (2013.01); *H01L 29/4236* (2013.01); *H01L 29/407* (2013.01); *H01L 29/41766* (2013.01); *H01L 29/66727* (2013.01); *H01L 29/66734* (2013.01); *H01L 21/22* (2013.01); *H01L 21/265* (2013.01); *H01L 29/7813* (2013.01); *H01L 21/2236* (2013.01); *H01L 21/26513* (2013.01); *H01L 21/31111* (2013.01); *H01L 29/0657* (2013.01); *H01L 29/0696* (2013.01); *H01L 29/0865* (2013.01); *H01L 29/1095* (2013.01); *H01L 21/26586* (2013.01)

(72) Inventors: **Johannes Georg Laven**, Taufkirchen (DE); **Maria Cotorogea**, Taufkirchen (DE); **Hans-Joachim Schulze**, Taufkirchen (DE); **Haybat Itani**, Villach (AT); **Erich Griebel**, Dorfen (DE); **Andreas Haghofer**, Villach (AT)

(21) Appl. No.: **16/828,665**

(22) Filed: **Mar. 24, 2020**

Related U.S. Application Data

(63) Continuation of application No. 16/110,508, filed on Aug. 23, 2018, now Pat. No. 10,629,676, which is a continuation of application No. 15/589,531, filed on May 8, 2017, now abandoned, which is a continuation of application No. 13/963,312, filed on Aug. 9, 2013, now Pat. No. 9,666,663.

Publication Classification

(51) **Int. Cl.**
H01L 29/06 (2006.01)
H01L 21/265 (2006.01)
H01L 29/40 (2006.01)
H01L 29/417 (2006.01)
H01L 29/66 (2006.01)
H01L 21/22 (2006.01)
H01L 29/78 (2006.01)

(57) **ABSTRACT**

A semiconductor device includes a plurality of first and second stripe-shaped cell trench structures formed in a semiconductor substrate and extending lengthwise in parallel with one another. Each stripe-shaped cell trench structure includes a buried electrode and an insulator layer between the buried electrode and the semiconductor substrate. A recess is formed in the insulator layer along a sidewall of one or more of the first stripe-shaped cell trench structures and vertically extends to a corresponding heavily doped contact zone. An electrically conductive material disposed in each recess contacts the corresponding buried electrode, a corresponding source zone and a corresponding heavily doped contact zone at the sidewall. Two or more of the first stripe-shaped cell trench structures are interposed between neighboring ones of the second stripe-shaped cell trench structures. Source zones alternate with portions of body zones in a lateral direction parallel to the stripe-shaped cell trench structures.




FIG 1A




FIG 1B




FIG 1C




FIG 1D




FIG 2




FIG 3A




FIG 3B





FIG 3C



**SEMICONDUCTOR DEVICE WITH
STRIPE-SHAPED CELL TRENCH
STRUCTURES AND RECESSED CONTACTS
AND METHOD OF MANUFACTURING
THEREOF**

BACKGROUND

[0001] Semiconductor devices based on vertical IGFET (insulated gate field effect transistor) cells include cell trench structures with buried electrodes and semiconductor mesas between the cell trench structures. Typically a photolithographic mask defines placement and size of the cell trench structures and another photolithographic mask defines placement and size of contact structures providing electric contacts to impurity zones in the semiconductor mesas. Other approaches rely on forming the contact structures self-aligned to the cell trench structures. It is desirable to provide semiconductor devices with narrow semiconductor mesas and small distances between neighboring cell trench structures in a reliable way and at low costs.

SUMMARY

[0002] According to an embodiment, a method of manufacturing a semiconductor device is provided. First and second cell trench structures are provided that extend from a first surface into a semiconductor substrate. The first cell trench structure includes a first buried electrode and a first insulator layer between the first buried electrode and a semiconductor mesa separating the first and second cell trench structures. A capping layer is provided that covers the first surface. The capping layer is patterned to form an opening having a minimum width that is larger than a thickness of the first insulator layer. The opening exposes a first vertical section of the first insulator layer at the first surface. An exposed portion of the first insulator layer is removed to form a recess between the semiconductor mesa and the first buried electrode. A contact structure is provided in the opening and the recess.

[0003] According to another embodiment, a method of manufacturing a semiconductor device includes introducing first and second cell trenches from a first surface into a semiconductor substrate, wherein first semiconductor mesas are formed between first and second cell trenches and second semiconductor mesas are formed between the first cell trenches. A first insulator layer is provided that lines at least sidewalls of the first cell trenches. First buried electrodes are provided in the first cell trenches on the first insulator layer. A capping layer is provided that covers the first surface. The capping layer is patterned to form first and second openings having a minimum width that is larger than a thickness of the first insulator layer. The first openings expose first vertical sections of the first insulator layers adjoining the first semiconductor mesas, respectively. The second openings expose the first buried electrodes of first cell trenches located between second semiconductor mesas. Exposed portions of the first insulator layers are removed to form recesses between the first semiconductor mesas and adjoining ones of the first buried electrodes. Conductive material is deposited to form, in the recesses and the first openings, first contact structures and second contact structures in the second openings.

[0004] Another embodiment refers to a semiconductor device with first and second cell trench structures extending

from a first surface into a semiconductor substrate. First semiconductor mesas separate first and second cell trench structures and second semiconductor mesas separate first cell trench structures. The first cell trench structures include a first buried electrode and a first insulator layer respectively, wherein first vertical sections of the first insulator layers separate the first buried electrodes from the first semiconductor mesas. A capping layer is located on the first surface. The semiconductor device includes first contact structures, wherein each first contact structure includes a first section in an opening of the capping layer and a second section between one of the first semiconductor mesas and one of the first buried electrodes directly adjoining the respective first semiconductor mesa.

[0005] Those skilled in the art will recognize additional features and advantages upon reading the following detailed description and on viewing the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0006] The accompanying drawings are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification. The drawings illustrate the embodiments of the present invention and together with the description serve to explain principles of the embodiment. Other embodiments and intended advantages will be readily appreciated as they become better understood by reference to the following detailed description.

[0007] FIG. 1A is a schematic cross-sectional view of a portion of a semiconductor substrate after providing an etch mask.

[0008] FIG. 1B is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 1A after providing openings in a capping layer by using the etch mask.

[0009] FIG. 1C is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 1B after forming recesses between first cell trench structures and first semiconductor mesas.

[0010] FIG. 1D is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 1C after providing solid contact structures filling the openings and the recesses.

[0011] FIG. 2 is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 1C after providing contact structures with voids in the openings and the recesses.

[0012] FIG. 3A shows a portion of a semiconductor substrate after providing recesses between a first buried electrode and first semiconductor mesas.

[0013] FIG. 3B shows the semiconductor substrate portion of FIG. 3A after widening the recesses.

[0014] FIG. 3C illustrates the semiconductor substrate portion of FIG. 2B after providing contact structures in the openings and widened recesses.

[0015] FIG. 4A is a schematic perspective view of a portion of semiconductor device in accordance with an embodiment related to an IGBT.

[0016] FIG. 4B illustrates a cross section of the semiconductor devices of FIG. 4A along section line B.

[0017] FIG. 4C illustrates a section of the semiconductor devices of FIG. 4A along cross section line C.

[0018] FIG. 4D illustrates a section of the semiconductor devices of FIG. 4A along cross section line D.

DETAILED DESCRIPTION

[0019] In the following detailed description, reference is made to the accompanying drawings, which form a part hereof, and in which are shown by way of illustrations specific embodiments in which the invention may be practiced. It is to be understood that other embodiments may be utilized and structural or logical changes may be made without departing from the scope of the present invention. For example, features illustrated or described for one embodiment can be used on or in conjunction with other embodiments to yield yet a further embodiment. It is intended that the present invention includes such modifications and variations. The examples are described using specific language that should not be construed as limiting the scope of the appending claims. The drawings are not scaled and are for illustrative purposes only. For clarity, the same elements have been designated by corresponding references in the different drawings if not stated otherwise.

[0020] The terms “having”, “containing”, “including”, “comprising” and the like are open and the terms indicate the presence of stated structures, elements or features but not preclude additional elements or features. The articles “a,” “an” and “the” are intended to include the plural as well as the singular, unless the context clearly indicates otherwise. The term “electrically connected” describes a permanent low-ohmic connection between electrically connected elements, for example a direct contact between the concerned elements or a low-ohmic connection via a metal and/or highly doped semiconductor. The term “electrically coupled” includes that one or more intervening element(s) adapted for signal transmission may be provided between the electrically coupled elements, for example elements that are controllable to temporarily provide a low-ohmic connection in a first state and a high-ohmic electric decoupling in a second state.

[0021] The Figures illustrate relative doping concentrations by indicating “-” or “+” next to the doping type “n” or “p”. For example, “n⁻” means a doping concentration that is lower than the doping concentration of an “n”-doping region while an “n⁺”-doping region has a higher doping concentration than an “n”-doping region. Doping regions of the same relative doping concentration do not necessarily have the same absolute doping concentration. For example, two different “n”-doping regions may have the same or different absolute doping concentrations.

[0022] FIGS. 1A to 1D refer to a semiconductor substrate **500a** consisting of or containing a semiconductor layer **100a** of a single-crystalline semiconductor material. The single-crystalline semiconductor material may be silicon Si, silicon carbide SiC, germanium Ge, a silicon germanium crystal Site, gallium nitride GaN or gallium arsenide GaAs. The semiconductor substrate **500a** may be a silicon wafer from which a plurality of identical semiconductor dies is obtained. The semiconductor layer **100a** has a planar first surface **101** and a second surface **102** parallel to the first surface **101**. The normal to the first and second surfaces **101**, **102** defines a vertical direction and directions orthogonal to the vertical direction are lateral directions.

[0023] In at least a portion of the semiconductor substrate **500a**, a first layer of a first conductivity type may be formed that directly adjoins the first surface **101**. The first layer of the first conductivity type may form a planar interface with a layer of a second, complementary conductivity type that separates the first layer of the first conductivity type from a

second layer of the first conductivity type. The interfaces between the layers may be parallel to the first surface **101**.

[0024] The first conductivity type may be the n type and the second conductivity type may be the p type as illustrated in the Figures. According to other embodiments the first conductivity type may be the p type and the second conductivity type may be the n type. Outside the illustrated portion, the semiconductor layer **100a** may include further impurity zones, intrinsic zones, as well as dielectric and conductive structures that may be configured to form electric circuits.

[0025] First and second cell trench structures **510**, **520** extend from the first surface **101** into the semiconductor substrate **500a**, wherein buried edges of the first and second cell trench structures have a greater distance to the first surface **101** than a pn junction between the layer of the second conductivity type and the second layer of the first conductivity type. The cell trench structures **510**, **520** provide segments in the first layer of the first conductivity type and the layer of the second conductivity type such that semiconductor mesas **150** between the first and second cell trench structures **510**, **520** have a layered structure with source zones **110** of the first conductivity type directly adjoining the first surface **101** and body zones **115** of the second conductivity type separating the source zones **110** from portions of a drift layer **120** of the first conductivity type.

[0026] The first cell trench structures **510** include at least a first buried electrode **515** and a first insulator layer **516** separating the first buried electrode **515** from the semiconductor material of the semiconductor substrate **500a** outside the first and second cell trench structures **510**, **520**,

[0027] Each second cell trench structure **520** includes a second buried electrode **525** and a second insulator layer **526** separating the second buried electrode **525** from the semiconductor material of the semiconductor substrate **500a** outside the cell trench structures **510**, **520**. At least one of the first and second cell trench structures **510**, **520** may include a further buried electrode dielectrically insulated from the respective first or second buried electrode **515**, **525**.

[0028] The first and second cell trench structures **510**, **520** may have the same vertical and lateral dimensions. According to other embodiments the first cell trench structures **510** are wider or narrower than the second cell trench structures **520**. Alternatively or in addition, the vertical extension of the first cell trench structures **510** exceeds or falls below the vertical extension of the second cell trench structures **520**. According to an embodiment, the vertical extension of both the first and the second cell trench structures **510**, **520** may be in a range from 500 nm to 20 μm , e.g. in a range from 2 μm to 7 μm .

[0029] The first and second buried electrodes **515**, **525** and, if applicable, the further buried electrode(s) may be provided from one or more conductive materials including polycrystalline silicon (polysilicon), which may be heavily doped, metal silicides, carbon C, metals, e.g. copper or tungsten, metal alloys, metal nitrides, metal silicides or other metal compounds, e.g. titanium nitride TiN, titanium tungstenide TiW, tantalum nitride TaN and others. For example, the first, the second, or both buried electrodes **515**, **516** have a layered structure including two or more layers of the above-mentioned materials. The first and second buried electrodes **515**, **516** may have the same structure and may

contain the same materials or may have different structures and/or contain different materials.

[0030] The first and second insulator layers **516**, **526** may have the same thickness or may have different thicknesses. For example, the first insulator layer **516** may be thicker than the second insulator layer **526**. The first and second insulator layers **516**, **526** may be based on the same materials or may consist of or may include different materials such as semiconductor oxides, e.g. silicon oxide, silicon nitride, alumina, and hafnium oxide, by way of example. According to an embodiment, at least one of the first and second insulator layers **516**, **526** has a layered structure including one or more different dielectric materials. A thickness of the first and second insulator layers may be between 30 nm and 200 nm, e.g. in the range between 80 nm and 120 nm. The second cell trench structure **520** may include a capping dielectric **210** between the first surface **101** and the second buried electrode **525**. The first cell trench structure **510** may or may not include a structure corresponding to the capping dielectric **210**.

[0031] The first and second buried electrodes **515**, **525** may be electrically connected to each other. According to the illustrated embodiment the first and second buried electrodes **515**, **525** are electrically separated from each other and can be connected to different signals or potentials. A potential applied to the second buried electrodes **525** may control the charge carrier distribution in the adjoining body zones **115** such that along the second insulator layers **526** a conductive channel may be formed when the potential applied to the second buried electrodes **525** exceeds a predefined threshold voltage. Sections of the second insulator layers **526** adjoining the body zones **115** are effective as gate dielectrics.

[0032] A capping layer **220** is provided on the first surface **101** and covers the first and second cell trench structures **510**, **520** as well as the semiconductor mesas **150**. The capping layer **220** includes one or more dielectric layers, each layer provided, for example, from deposited semiconductor oxide, for example a silicon oxide generated by using TEOS (tetraethyl orthosilicate) as precursor material, other silicon oxides, silicon nitride, or silicon oxynitride. The thickness of the capping layer **220** may be approximately uniform and may range from about 100 nm to 1 μm , by way of example.

[0033] A photo resist layer is deposited on the capping layer **220** and patterned by photolithographic techniques to form an etch mask **410**.

[0034] FIG. 1A shows the capping layer **220** covering the first and second cell trench structures **510**, **520** and the semiconductor mesas **150** between the first and second cell trench structures **510**, **520**. Mask openings **405** in the etch mask **410** expose portions of the capping layer **220** in the vertical projection of first vertical sections of the first insulator layers **516**, wherein the first vertical sections adjoin such semiconductor mesas **150** that separate first and second cell trench structures **510**, **520**. The mask openings **405** also expose portions of the capping layer **220** in the vertical projection of portions of the semiconductor mesas **150** directly adjoining the concerned sections of the first insulator layers **516** as well as portions of the capping layer **220** in the vertical projection of a portion of the first buried electrode **515** directly adjoining the concerned sections of the first insulator layer **516**.

[0035] The etch mask **410** covers portions of the capping layer **220** in the vertical projection of the second cell trench

structures **520** as well as portions of the capping layer **220** in the vertical projection of second vertical sections of the first insulator layers **516** adjoining semiconductor mesas **150** between first cell trench structures **510**. Using the etch mask **410**, a predominantly anisotropic etch recesses the exposed portions of the capping layer **220**. The etch removes the material of the capping layer **220** at a higher rate than the single crystalline semiconductor material of the semiconductor mesas **150** and the material of the first buried electrodes **515**. The etch process may include an endpoint detection sensitive to reaching at least one of the semiconductor mesas **150**, the first vertical sections of the first insulator layer **516**, and the first buried electrode **515**.

[0036] FIG. 1B shows openings **305x** in the capping layer **220** after the etching has reached the first surface **101**. The openings **305x** expose the first vertical sections of the first insulator layers **516**, portions of the first buried electrodes **515** directly adjoining the concerned sections of the first insulator layers **516** and portions of semiconductor mesas **150** directly adjoining the concerned sections of the first insulator layers **516**.

[0037] After detecting the endpoint, an in-situ over etch may be performed for a predefined time to recess the exposed first vertical sections of the first insulator layers **516**. The recess etch removes exposed portions of the first insulator layers **516** up to a second distance to the first surface **101**, which is greater than a first distance between the first surface **101** and the interface between the source and body zones **110**, **115** and which is smaller than a third distance between the first surface **101** and the interface between the body zones **115** and the drift layer **120**. The second distance may be at least 200 nm and at most 1 μm , e.g. between 400 μm and 600 μm . The material of the first insulator layer **516** is recessed at a removal rate that may be at least five times the removal rate for the semiconductor material and/or the material of the first buried electrode **515**.

[0038] FIG. 1C shows the resulting recesses **305y** between the concerned first buried electrodes **515** and the concerned semiconductor mesas **150**. Due to the selectivity of the etch of the insulator layer **516**, the recesses are self-aligned within the openings **305x** to the first cell trench structures **510** and the concerned semiconductor mesas **150**. In the layout, the width of the semiconductor mesas **150** may be further reduced, e.g. to below 400 nm.

[0039] Whereas conventional approaches provide a first etch process through the material of a capping layer and a second etch process for providing contact grooves in the semiconductor materials of semiconductor mesas and buried electrodes, the present embodiment provides one combined etch for openings in the capping layer and recesses along the semiconductor mesas **150**. The combined etch may be performed as one in-situ process at the same tool.

[0040] One or more conductive materials are deposited to form a first electrode structure **310** on the side of the semiconductor substrate **500a** defined by the first surface **101** as well as contact structures **305** electrically connecting the first electrode structure **310** with the first buried electrodes **515**, the body zones **115** and the source zones **110** of the semiconductor mesas **150** that separate first and second cell trench structures **510**, **520**. Providing the first electrode structure **310** may include successive deposition of one or more conductive materials.

[0041] According to an embodiment, a barrier layer **311** having a uniform thickness in the range of 5 nm to 100 nm

may be deposited. The barrier layer may bar metal atoms from diffusing into the semiconductor substrate **500a** and may be a layer of titanium nitride TiN, tantalum nitride TaN, titanium tungstenide TiW, titanium Ti or tantalum Ta, or may include these materials.

[0042] A main layer **312** may be deposited on the barrier layer **311**. The main layer **312** may consist of or contain tungsten or tungsten based metals such as titanium tungstenide TiW, heavily doped polysilicon, carbon C, aluminum Al, copper Cu or alloys of aluminum and copper, such as AlCu or AlSiCu. At least one of the layers may be provided with a porous structure or may be deposited in a way to form voids or small cavities within the recesses **305y** and/or the openings **305x**. Voids and cavities in the recesses **305y**, and openings **305x** reduce mechanical stress.

[0043] FIG. 1D shows the first electrode structure **310** including the barrier layer **311** and the main layer **312**. The thickness of the barrier layer **311** may be less than a half of the width of the recess **305y** in FIG. 1C. According to another embodiment, the barrier layer **311** fills the recess **305y** completely. The materials of the main layer **312** and the barrier layer **311** may fill the openings **305x** in the capping layer **220** and the recesses **305y**, in the semiconductor portion **100** completely to form solid contact structures **315** as shown in FIG. 1D.

[0044] FIG. 2 is related to other embodiments with the main layer **312** leaving voids **395** in the recesses **305y** and the openings **305x**.

[0045] FIGS. 3A to 3C refer to an embodiment that includes a widening of the recesses **305y**. In first sections of first insulator layers **516** between first buried electrodes **515** and such semiconductor mesas **150** that are formed between first and second cell trench structures **510**, **520** and that are exposed by openings **305x** in a capping layer **220**, recesses **305y** may be formed between the first buried electrodes **515** and the concerned semiconductor mesas **150**. An etch selectivity at which the material of the buried first electrode **515** is removed with respect to the material of semiconductor mesa **150** may be at least 5:1. The etch mask may be removed.

[0046] FIG. 3A shows the openings **305x** in the capping layer **220** and the recesses **305y** between the first buried electrodes **515** and the concerned semiconductor mesas **150**. Contact openings **305** include an opening **305x** and a recess **305y**, respectively. A first etch step forms the opening **305** in the capping layer **220** and may stop at the first surface **101**. A second etch step that may use the same etch process over-etches the first insulator layer **316** for a predetermined time. Using a different etch process, a third etch step widens at least the openings of the recesses **305y** at the expense of either the adjoining semiconductor mesas **150** or the adjoining portions of the first buried electrodes **515** or both. For example, a short isotropic silicon etch may remove polycrystalline material, which may be used for the first buried electrodes **515**, at a higher etch rate than the single crystalline semiconductor material of the semiconductor mesas **150**.

[0047] According to another embodiment, a first etch process forms the openings **305** in the capping layer **220** and stops at the first surface **101**. A second etch step forms wide recesses **305y** by using an etch process with lower selectivity than the first etch process such that a certain amount of the first buried electrodes **515** is recessed contemporaneously with the material of the first insulator layer **516**. As a result,

the width of the semiconductor mesas **150** can be essentially maintained such that a channel portion along the second cell trench structure **520** remains unaffected from processes applied at the recesses **305y**.

[0048] According to another embodiment, the etch selectivity of the process for generating the recesses **305y** is gradually reduced with time such that the sidewall angles of the recess **305y** become less steep. In both cases, the etch rate may be higher in the polycrystalline silicon material, which may be used for the first buried electrodes **515**, than in the single crystalline semiconductor material of the semiconductor mesas **150**. Processes widening the recesses **305y** ease the later filling of the recesses **305y** with the one or more contact materials without significantly reducing the dimensions of the semiconductor mesas **150**.

[0049] According to an embodiment, an implant may be performed through the sidewalls of the recesses **305y** to reduce a contact resistance to the body zones **115** and the risk of latch-up effects. For example, a BF2 implant may be performed. The implant may be activated through an RTA (rapid thermal anneal) to form heavily doped contact zones **117** along the sidewall portions of the semiconductor mesas **150** exposed by the widened recesses **305y**. The contact zones **117** have the second conductivity type and do not reach the second cell trench structures **520** such that a variation of a threshold voltage due to impurities of the BF2 implant reaching the channel along the second insulator layer **526** can be avoided.

[0050] According to another embodiment, a plasma implant may be performed through the sidewalls of the widened recesses **305y** to form conformal contact zones **117**. Since the plasma implant counter-dopes portions of the source zones **110**, the source zones **110** are provided with a sufficient high net impurity concentration.

[0051] FIG. 3B shows an angled implant **380** for introducing impurities of the second conductivity type into exposed sidewall portions of the semiconductor mesas **150** and the heavily doped contact zones **117** of the second conductivity type emerging from the angled implant **380** after anneal. In the case of tapered recesses **305y**, the implant **380** may be an orthogonal implant perpendicular to the first surface **101**. Otherwise, the implant angle with respect to the normal may be greater 0 degrees.

[0052] A barrier layer **311** may be deposited on the capping layer **220**, wherein the barrier layer **311** lines the combined contact openings **305**. A main layer **312** is deposited that may fill the contact openings **305** completely or that may leave voids in the contact openings **305**.

[0053] FIG. 3C shows the first electrode structure **310** and the contact structures **315** formed in the contact openings **305**. A slope of the contact openings **305** at a side oriented to the concerned semiconductor mesa **150** is steeper than a slope at the opposing side oriented to the concerned first buried electrode **515**.

[0054] FIGS. 4A to 4D illustrate a semiconductor device **500** obtained from one of a plurality of identical semiconductor dies processed as a portion of the semiconductor substrate **500a** of FIGS. 1A to 1D. The semiconductor device **500** may be a power switching device, e.g. an IGBT (insulated gate bipolar transistor) e.g. a PT-IGBT (punch through IGBT) or an IGFET.

[0055] The semiconductor device **500** includes a semiconductor portion **100** with a first surface **101** and a second surface **102** parallel to the first surface **101**. The semicon-

ductor portion **100** is provided from a single-crystalline semiconductor material, for example silicon Si, silicon carbide SiC, germanium Ge, a silicon germanium crystal SiGe, gallium nitride GaN or gallium arsenide GaAs. A minimum distance between the first and second surfaces **101**, **102** is selected to achieve a specified voltage blocking capability of the drift zone **120**, for example 90 to 110 μm for a 1200 V blocking IGBT. Other embodiments related to higher blocking devices or PT-IGBT device approaches may provide semiconductor portions **100** with a thickness of several 100 μm distances between **101** and **102**. Low voltage IGFETs may be thinner, e.g. at least some 10 μm .

[0056] The semiconductor portion **100** may have a rectangular shape with an edge length in the range of several millimeters. The normal to the first and second surfaces **101**, **102** defines a vertical direction and directions orthogonal to the normal direction are lateral directions.

[0057] First and second cell trench structures **510**, **520** extend from the first surface **101** into the semiconductor portion **100**. The first and second cell trench structures **510**, **520** may have the same vertical dimensions and the same lateral dimensions. According to other embodiments, the lateral and/or vertical dimensions of the first and second cell trench structures **510**, **520** differ from each other. The vertical extension may be in the range from 500 nm to 20 μm , e.g. from 2 μm to 7 μm . The lateral width may be less than 2 μm , e.g. less than 1.2 μm .

[0058] The first cell trench structures **510** comprise first buried electrodes **515** and first insulator layers **516** separating the first buried electrodes **515** from the semiconductor material outside the first and second cell trench structures **510**, **520**. The first insulator layers **516** may have a uniform thickness in a range from 50 nm to 150 nm, e.g. between 80 nm and 120 nm, by way of example. The first cell trench structures **510** may or may not include further conductive structures, e.g. a further electrode dielectrically insulated from the first buried electrodes **515**.

[0059] The second cell trench structures **520** include second buried electrodes **525** and second insulator layers **526** dielectrically insulating the second buried electrodes **525** from the semiconductor material outside the first and second cell trench structures **510**, **520**. The second cell trench structures **520** may include a further conductive structure, for example a further electrode dielectrically insulated from the second buried electrodes **525**. The number of first and second cell trench structures **510**, **520** may be equal. Other embodiments provide more first cell trench structures **510** than second cell trench structures **520**. For example, at least two first cell trench structures **510** are provided between two second cell trench structures **520**, respectively. The semiconductor mesas **150** between second cell trench structures **520** may or may not be connected to the source potential.

[0060] The first and second cell trench structures **510**, **520** may be parallel stripes arranged in a regular pattern. According to other embodiments, the lateral cross-sectional areas of the cell trench structures **510**, **520** may be circles, ellipses, ovals or rectangles, e.g. squares, with or without rounded corners, or rings. For example, two or three of the first and second cell trench structures **510**, **520** may form an arrangement with two or three concentric rings, wherein the rings may be circles, ellipses, ovals, or rectangles, e.g. squares with or without rounded corners.

[0061] IGBT cells may be formed in the semiconductor portion **100** at a side oriented to the first surface **101**,

wherein active areas of the IGBT cells are formed in first semiconductor mesas **150a** separating one first cell trench structure **510** and one second cell trench structure **520**, respectively. In the first semiconductor mesas **150a**, source zones **110** of the first conductivity type may directly adjoin the first surface **101**. The source zones **110** form first pn junctions with body zones **115** of the second conductivity type, wherein interfaces between the source and body zones **110**, **115** run approximately parallel to the first surface **101** at a first distance $d1$. The body zones **115** form second pn junctions with a drift layer **120** of the first conductivity type at a third distance $d3$ to the first surface **101**. The first and second cell trench structures **510**, **520** extend through the source zones **110** and the body zones **115** into the drift layer **120**.

[0062] The illustrated embodiment refers to a fieldstop IGBT and the semiconductor portion **100** includes a collector layer **130** that directly adjoins the second surface **102**. The collector layer **130** may be a contiguous layer of the second conductivity type. According to other embodiments related to, e.g. reverse conducting IGBTs, the collector layer **130** may include first portions of the first conductivity type and second portions of the second conductivity type, wherein the first and second portions alternate in one lateral direction or in both lateral directions. A mean net impurity concentration in the collector layer **130** may be at least $1 \times 10^{16} \text{ cm}^{-2}$, for example at least $5 \times 10^{17} \text{ cm}^{-3}$.

[0063] A second electrode structure **320** directly adjoins the second surface **102**. The second electrode structure **320** is electrically connected to the collector layer **130** and may consist of or contain, as main constituent(s) aluminum Al, copper Cu, or alloys of aluminum or copper, such as AlSi, AlCu or AlSiCu. According to other embodiments, the collector electrode **320** may contain one, two, three or more sub-layers, wherein each sub-layer contains, as main constituent(s), at least one of nickel Ni, titanium Ti, silver Ag, gold Au, tungsten W, platinum Pt and/or palladium Pd. For example, a sub-layer may contain a metal silicide, a metal nitride, or a metal alloy containing Ni, Ti, Ag, Au, W, Pt, and/or Pd. For IGBTs, the second electrode structure **320** provides a collector electrode that may provide or may be electrically connected to a collector terminal C of the semiconductor device **500**.

[0064] In the drift layer **120**, a field stop layer **128** may be provided between the collector layer **130** and a drift zone **121**. A mean net impurity concentration in the field stop layer **128** may be between $5 \times 10^{15} \text{ cm}^{-3}$ and $1 \times 10^{17} \text{ cm}^{-3}$. The mean net impurity concentration in the drift zone **121** is lower than in the field stop layer **128**. According to an embodiment, the mean net impurity concentration in the field stop layer **128** exceeds at least five times the mean net impurity concentration in the drift zone **121**. The mean net impurity concentration in the drift zone **121** may be between $5 \times 10^{12} \text{ cm}^{-3}$ and $5 \times 10^{14} \text{ cm}^{-3}$, by way of example. For IGFETs, a heavily doped contact layer of the first conductivity type replaces the collector layer **130** and the second electrode structure **320** provides a drain electrode that may provide or may be electrically connected to a drain terminal of the semiconductor device **500**.

[0065] The second buried electrodes **525** provide insulated gate electrodes Ga. A potential applied to the insulated gate electrodes Ga controls a minority charge carrier distribution in channel portions **115a** of the body zones **115**, wherein the channel portions **115a** adjoin the second cell trench struc-

tures **520** between the source zones **110** and the drift layer **120**. If in a forward biased mode the potential applied to the insulated gate electrodes Ga exceeds a predefined threshold voltage, inversion channels of the first conductivity type are formed in the body zones **115** along the second insulator layers **526**, which are effective as gate dielectrics, and an on-state current flows between the source zones **110** and the drift layer **120**. The insulated gate electrodes Ga may be electrically connected to a third electrode structure **330** that may provide or may be electrically connected or coupled to a gate terminal G of the semiconductor device **500**.

[0066] Second semiconductor mesas **150b** between first cell trench structures **510** may or may not include source zones **110**. In the latter case, the body zones **115** may extend between the first surface **101** and the drift layer **120**.

[0067] The first cell trench structures **510** provide buried source electrodes S that may be electrically connected to an emitter terminal E of the semiconductor device **500**. The insulated gate electrodes Ga are insulated from the buried source electrodes S. At least the second cell trench structures **520** may include a capping dielectric **210** between the first surface **101** and the second buried electrodes **525** to reduce an overlap between the insulated gate electrodes Ga and the source zones **110**. Other embodiments may provide contacts to some or all of the second semiconductor mesas **150**.

[0068] A dielectric capping layer **220** may dielectrically insulate at least the second cell trench structures **520** and the second semiconductor mesas **150b** from a first electrode structure **310** disposed at a side defined by the first surface **101**. First contact structures **315** electrically connect the first electrode structure **310** with the first semiconductor mesas **150a** and such first cell trench structures **510** that directly adjoin the first semiconductor mesas **150a**. Second contact structures **316** electrically connect the first electrode structure **310** with other first cell trench structures **510** not directly adjoining the first semiconductor mesas **150a**.

[0069] Each of the first contact structures **315** includes a first section **315a** in an opening of the capping layer **220** and a second section **315h** between a first semiconductor mesa **150a** and a first cell trench structure **510** directly adjoining the first semiconductor mesa **150a**. The second section **315b** extends from the first surface **101** into the semiconductor portion **100**. A second distance d_2 between the first surface **101** and the buried edge of the second section **315b** is greater than the first distance d_1 and smaller than the third distance d_3 .

[0070] The second sections **315b** of the first contact structures **315** may have approximately vertical sidewalls. According to an embodiment, the sidewalls for the second sections **315b** taper with increasing distance to the first surface **101**.

[0071] According to an embodiment, first sidewalls of the second sections **315b** of the first contact structures **315** are tilted to the first surface **101** and directly adjoin the first semiconductor mesas **150a**. Second sidewalls of the second sections **315b** of the first contact structures **315** may be tilted to the first surface **101** and directly adjoin the first buried electrodes **510**. The first sidewall oriented to the first semiconductor mesas **150** and the second sidewalls oriented to the first buried electrodes **510** may have identical slope angles. The second sidewalls may deviate to a higher degree from a normal to the first surface **101** than the first sidewalls of the second sections **315b** of the first contact structures **315**.

[0072] The second sections **315b** of the first contact structures **315** are located in the vertical projection of first sections of the first insulator layers **516**. The first insulator layers **516** may have a uniform width, wherein the width of the first insulator layers **516** may be equal to or less than a width of the second sections **315h** of the first contact structures **315**. The first contact structures **315** are deep enough to provide a direct contact to the body zones **115**. [0073] Heavily doped contact zones **117** may be formed in the body zones **115** of the first semiconductor mesas **150a** along the interfaces to the first contact structures **315**. The second electrode structure **310** as well as the third electrode structure **330** may include at least one barrier layer **311**, **331**, respectively. The barrier layer may have a uniform thickness in the range of 5 nm to 100 nm and may consist of or include a layer of titanium nitride TiN, tantalum nitride TaN, titanium tungstenide TiW, titanium Ti or tantalum Ta, by way of example. The main layers **312**, **332** may consist of or contain tungsten or tungsten-based metals like titanium tungstenide TiW, heavily doped polysilicon, carbon C, aluminum Al, copper Cu or alloys of aluminum and copper, for example AlCu or AlSiCu.

[0074] The first and second contact structures **315**, **316** may be solid contact structures, may include a porous layer or may have voids as shown in FIG. 2. The source zones **110** may be provided as narrow stripes and may alternate with portions of the body zones **115** in a lateral direction parallel to stripe shaped first and second cell trench structures **510**, **520**.

[0075] Uncertainties and inequalities of different lithographic layers resulting in a misalignment between contact structures and semiconductor mesas limit a minimal mesa width conventionally at about 600 nm instead, the semiconductor device **500** of FIGS. 4A to 4D facilitates narrowing the width of the semiconductor mesas to less than 300 nm, for example less than 200 nm.

[0076] Further embodiments concern layout modifications of the first and second trench structures **510**, **520** to further reduce an effective channel width for increasing short-circuit ruggedness, e.g. by segmenting the second cell trench structures **520** or by increasing locally a thickness of the second insulator layers **526**.

[0077] Although specific embodiments have been illustrated and described herein, it will be appreciated by those of ordinary skill in the art that a variety of alternate and/or equivalent implementations may be substituted for the specific embodiments shown and described without departing from the scope of the present invention. This application is intended to cover any adaptations or variations of the specific embodiments discussed herein. Therefore, it is intended that this invention be limited only by the claims and the equivalents thereof.

What is claimed is:

1. A semiconductor device, comprising:
 - a plurality of source zones of a first conductivity type formed in a semiconductor substrate;
 - a plurality of body zones of a second conductivity type opposite the first conductivity type formed in the semiconductor substrate below the plurality of source zones;
 - a plurality of heavily doped contact zones formed in the body zones;
 - a plurality of first stripe-shaped cell trench structures formed in the semiconductor substrate and extending lengthwise in parallel with one another, each first

- stripe-shaped cell trench structure comprising a first buried electrode and a first insulator layer between the first buried electrode and the semiconductor substrate;
- a plurality of second stripe-shaped cell trench structures formed in the semiconductor substrate and extending lengthwise in parallel with one another, each second stripe-shaped cell trench structure comprising a second buried electrode and a second insulator layer between the second buried electrode and the semiconductor substrate;
- a recess formed in the first insulator layer along a sidewall of one or more of the first stripe-shaped cell trench structures and vertically extending to the corresponding heavily doped contact zone; and
- an electrically conductive material disposed in each recess formed in the first insulator layer and contacting the corresponding first buried electrode, the corresponding source zone and the corresponding heavily doped contact zone at the sidewall,
- wherein two or more of the first stripe-shaped cell trench structures are interposed between neighboring ones of the second stripe-shaped cell trench structures,
- wherein the source zones alternate with portions of the body zones in a lateral direction parallel to the first and second stripe-shaped cell trench structures.
2. The semiconductor device of claim 1, wherein the sidewall of the one or more first stripe-shaped cell trench structures with the recess is tilted by less than 90 degrees with respect to a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend.
3. The semiconductor device of claim 1, wherein the first insulator has a width.
4. The semiconductor device of claim 1, wherein the width of each recess increases with increasing proximity to a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend.
5. The semiconductor device of claim 1, wherein the width of the first buried electrode in each first stripe-shaped cell trench structure with a recessed first insulator layer decreases with increasing proximity to a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend.
6. The semiconductor device of claim 5, wherein the width of the first buried electrode in each first stripe-shaped cell trench structure with a recessed first insulator layer is generally uniform below the recess.
7. The semiconductor device of claim 1, further comprising a capping layer formed on a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend, wherein the electrically conductive material disposed in each recess formed in the first insulator layer extends through openings in the capping layer to form part of an overlying contact structure.
8. The semiconductor device of claim 7, wherein the first buried electrode of one or more of the first stripe-shaped cell trench structures is electrically contacted by the contact

structure through an additional opening in the capping layer which is aligned with a top side of the first buried electrode.

9. The semiconductor device of claim 1, wherein the first buried electrodes are electrically coupled to a source potential, and wherein the second buried electrodes are electrically coupled to a gate potential.

10. The semiconductor device of claim 1, wherein the semiconductor device is an IGBT.

11. The semiconductor device of claim 1, wherein between neighboring ones of the source zones, a body zone extends to a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend.

12. The semiconductor device of claim 1, wherein interfaces between the source zones and the body zones run approximately parallel to a first surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend at a first distance, wherein a second distance between the first surface and an edge of the electrically conductive material at a bottom of each recess formed in the first insulator layer is greater than the first distance, wherein interfaces between the body zones and a drift layer of the first conductivity type run approximately parallel to the first surface at a third distance, and wherein the second distance is smaller than the third distance.

13. The semiconductor device of claim 1, wherein between first stripe-shaped cell trench structures of the plurality of first stripe-shaped cell trench structures for which the first buried electrode is contacted by the electrically conductive material through the recess formed in the corresponding first insulator layer, the buried electrode of at least one first stripe-shaped cell trench structure of the plurality of first stripe-shaped cell trench structures is contacted by the electrically conductive material only at a first main surface of the semiconductor substrate.

14. A method of manufacturing a semiconductor device, the method comprising:

- forming a plurality of source zones of a first conductivity type in a semiconductor substrate;
- forming a plurality of body zones of a second conductivity type opposite the first conductivity type in the semiconductor substrate below the plurality of source zones;
- forming a plurality of heavily doped contact zones in the body zones;
- forming a plurality of first stripe-shaped cell trench structures in the semiconductor substrate and extending lengthwise in parallel with one another, wherein each first cell trench structure comprises a first buried electrode and a first insulator layer between the first buried electrode and the semiconductor substrate;
- forming a plurality of second stripe-shaped cell trench structures in the semiconductor substrate and extending lengthwise in parallel with one another, wherein two or more of the first stripe-shaped cell trench structures are interposed between neighboring ones of the second stripe-shaped cell trench structures, wherein each second stripe-shaped cell trench structure comprises a second buried electrode and a second insulator layer between the second buried electrode and the semiconductor substrate;

forming a recess in the first insulator layer along a sidewall of one or more of the first stripe-shaped cell trench structures and vertically extending to the corresponding heavily doped contact zone; and

disposing an electrically conductive material in each recess formed in the first insulator layer so as to contact the corresponding first buried electrode, the corresponding source zone and the corresponding heavily doped contact zone at the sidewall,

wherein the source zones alternate with portions of the body zones in a lateral direction parallel to the first and second stripe-shaped cell trench structures.

15. The method of claim **14**, wherein forming the recess in the first insulator layer along a sidewall of the one or more first stripe-shaped cell trench structures comprises tilting the sidewall of the one or more first stripe-shaped cell trench structures by less than 90 degrees with respect to a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend.

16. The method of claim **15**, wherein tilting the sidewall of the one or more first stripe-shaped cell trench structures by less than 90 degrees with respect to the first main surface of the semiconductor substrate comprises removing a material of the buried first electrode at an etch selectivity with respect to a material of the semiconductor substrate of at least 5:1.

17. The method of claim **14**, wherein forming the recess in the first insulator layer along a sidewall of the one or more first stripe-shaped cell trench structures comprises decreas-

ing the width of each recess with decreasing proximity to a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend.

18. The method of claim **17**, wherein the width of the first buried electrode in each first stripe-shaped cell trench structure with a recessed first insulator layer is generally uniform below the recess.

19. The method of claim **14**, further comprising:
forming a capping layer on a first main surface of the semiconductor substrate into which the plurality of first stripe-shaped cell trench structures and the plurality of second stripe-shaped cell trench structures extend, wherein the electrically conductive material disposed in each recess formed in the first insulator layer extends through openings in the capping layer to form part of an overlying contact structure.

20. The method of claim **19**, further comprising:
electrically contacting the first buried electrode of one or more of the first stripe-shaped cell trench structures by the contact structure through an additional opening in the capping layer which is aligned with a top side of the first buried electrode.

21. The method of claim **14**, further comprising:
electrically coupling the first buried electrodes to a source potential; and
electrically coupling the second buried electrodes to a gate potential.

* * * * *