

Shur Strip® H914

Alkaline Paint Stripper

Shur Strip H-914 is an alkaline paint stripper formulated to remove vinyls, acrylics, most epoxies and alkyds from steel, plastic and nylon surfaces.

Tank Immersion

Shur Strip H-914 is a tank immersion material which is used between 20% and 50% by volume with water at 180°F to 210°F. Exact concentration will depend upon the particular paint base to be stripped. Stripping time varies from a few minutes to 20 minutes or more. Once again, the type of finish to be removed determines the exact exposure time. When the coating has been loosened, a pressure rinse is recommended to assure complete removal of any residue.

Notes On Use:

When preparing new solutions or adding to existing ones, slowly add to surface of solution while stirring to avoid splattering. Do not add large amounts of product to solution at any one time.

PAINT STRIPPERS

Technical Data

| | |
|-------------------------------|------------------------|
| physical Form | amber liquid |
| odor | bland |
| specific gravity | 1.210 @ 68 F |
| flash point | none |
| foaming tendency | slight |
| recommended diluent | water |
| maximum solubility | complete |
| rinsability | good |
| phosphate free | yes |
| normal working concentrations | 20% - 50% by vol |
| normal working temperatures | 180°F - 210°F |
| pH @ working concentrations | 13.8% per 20% solution |

Packaging Options

5 gallon pail
55 gallon drum
330 gallon tote tanks

Other Available TLS Products

Shur Draw® 420
Heavy-Duty semi synthetic drawing compound

Shur Cool® 5010
Low-foaming top of the line synthetic coolant for steel, stainless steel and aluminium

ID 240
Concentrated, industrial-strength liquid cleaner/degreaser.



T & SPECIALTY
Chemicals for Industry

300 AIR PARK ROAD · TUPELO, MISSISSIPPI 38801
662.842.8143 · FAX: 662.842.8583 · 800.882.5966
WWW.TLSPECIALTY.COM · SUPPORT@TLSPECIALTY.COM