


FLOOR

ARCHAIA™

GLAZED PORCELAIN FLOOR & GLAZED CERAMIC MOSAIC



| SIZES | | | Thickness | Sq. Ft./ Carton | Pieces/ Carton |
|-------|--------------------------------------|--|-----------|-----------------|----------------|
| | 20 x 20 Floor Tile | (19-11/16" x 19-11/16") (50.00 cm x 50.00 cm) | 3/8" | 18.83 | 7 |
| | 12 x 24 Floor Tile | (11-13/16" x 23-13/16") (30.00 cm x 60.48 cm) | 5/16" | 17.37 | 9 |
| | 13 x 13 Floor Tile | (13-1/8" x 13-1/8") (33.30 cm x 33.30 cm) | 5/16" | 17.85 | 15 |
| | 2 x 4 Herringbone Mosaic Dot-mounted | (14" x 12" Sheet) (35.56 cm x 30.48 cm Sheet) | 1/4" | 8.04 | 12 |

| APPLICATIONS | Target DCOF wet | Suitable |
|--|-----------------|----------|
| Dry & Level – Interior Floor | N/A | ✓ |
| Wet & Level – Interior Floor | ≥ 0.42 | ✓ |
| Shower Floors (Residential or Light Commercial) | ≥ 0.42 | ✓* |
| Exterior Floor Applications (Including pool decking & other wet areas with minimal footwear) | ≥ 0.60 | |
| Ramps & Inclines | ≥ 0.65 | |
| Walls/Backsplashes | N/A | ✓ |
| Countertops | N/A | ✓ |
| Pool Linings | N/A | ✓* |

A DCOF value of ≥0.42 is the standard for tiles specified for level interior spaces expected to be walked upon when wet, as stated in ANSI A1371-A326.3. For more information about DCOF and the DCOF AcuTest™, visit daltile.com/DCOF.

APPLICATION NOTES:
 Floor tile suitable for exterior applications in freezing and non-freezing climates, when proper installation methods are followed.
 Mosaic tile suitable for exterior applications in non-freezing climates, when proper installation methods are followed.
 * Mosaic tile only.

| TRIM | | | | |
|----------|--------|--------|----------------|--|
| Type | Number | Size | Pieces/ Carton | |
| Bullnose | P-43E9 | 3 x 13 | 20 | |

INSTALLATION

| Grout Joint Recommendation | Shade Variation |
|--|-----------------|
| Floor: 3/16" (Overlap should not exceed 33% when installing tile with a length 15" or greater in a staggered brick-joint pattern.) Mosaic: 1/8" | Random (V4) |

| PERFORMANCE CHARACTERISTICS | | | |
|-----------------------------|-------|--------------|---------------|
| | ASTM# | Floor Result | Mosaic Result |
| Water Absorption | C373 | < 0.5% | < 3.0% |
| Breaking Strength | C648 | > 275 lbs | > 250 lbs |
| Scratch Hardness | MOHS | 8.0 | 8.0 |
| Chemical Resistance | C650 | Resistant | Resistant |
| Abrasion Resistance | CI027 | 4 | 4 |

For additional information on test results, visit us at: daltile.com/information/TestResults.

NOTES

Since there are variations in all fired ceramic and natural products, tile and trim supplied for your particular installation may not match samples. Final confirmation should be made from actual tiles and trim prior to installation. Manufactured in accordance with ANSI A1371 standards.

Not for use on ramps. Water, oil, grease, improper drainage and certain footwear can create slippery conditions. Floor applications expected to be exposed to these conditions require extra caution in product selection.

For additional information refer to "Factors to Consider" at: daltile.com/Factors.

Random visuals enhance the natural beauty of this product. To achieve optimal results, all tile should be selected from multiple cartons and shading and graphic arrangement planned prior to installation.

Special consideration needs to be given when installing tiles greater than 15 inches. Please refer to daltile.com/LargeTiles for more information.

Use of a latex modified thin-set is recommended for installation. For more information, visit daltile.com.

| | |
|---|--|
| POST-CONSUMER RECYCLED MATERIALS | PRE-CONSUMER RECYCLED MATERIALS |
| MADE IN THE U.S.A. | REVEAL IMAGING® |

All or select items within this series meet the requirements for these qualifications. For more information, visit daltile.com.



7834 C.F. Hawn Freeway,
 Dallas, Texas 75217 | 1.800.933.TILE

To view the complete collection of Daltile® products and information, visit our website at daltile.com.

