



Solaris

Clear Silicone Encapsulant

Mix Ratio is 100A : 10B by Weight

Solaris is a low viscosity, water white clear silicone rubber compound designed for use in protection of electronic components and other assemblies.

Pot life is 120 minutes and cure time is 24 hours at 73°F/23°C. Please read Technical Bulletin and MSDS before using available at www.smooth-on.com.

Ingredients: Polysiloxanes

WARNING: KEEP AWAY FROM CHILDREN. Refer to the MSDS for further safety information. Do not ingest or apply to skin.

Net Weight: 10 lbs. (4.54 kgs.)

THIS IS PART A

SMOOTH-ON, INC. 2000 St. John Street, Easton, PA 18042 USA PHONE: 610-252-5800 FAX: 610-252-6200

IMPORTANT: This product has been tested to assure conformance to certain quality control standards. However, since the manufacturer has no control over actual application, no warranty is expressed or implied regarding the results to be obtained from the use thereof. User must determine suitability of this product for the intended application and assume all risk and liability in connection therewith.

FOR INDUSTRIAL USE ONLY: KEEP OUT OF REACH OF CHILDREN.

www.smooth-on.com



Solaris

Clear Silicone Encapsulant

Mix Ratio is 100A : 10B by Weight

Solaris is a low viscosity, water white clear silicone rubber compound designed for use in protection of electronic components and other assemblies.

Pot life is 120 minutes and cure time is 24 hours at 73°F/23°C. Please read Technical Bulletin and MSDS before using available at www.smooth-on.com.

Ingredients: Polysiloxanes

WARNING: KEEP AWAY FROM CHILDREN. Refer to the MSDS for further safety information. Do not ingest or apply to skin.

Net Weight: 10 lbs. (4.54 kgs.)

THIS IS PART A

SMOOTH-ON, INC. 2000 St. John Street, Easton, PA 18042 USA PHONE: 610-252-5800 FAX: 610-252-6200

IMPORTANT: This product has been tested to assure conformance to certain quality control standards. However, since the manufacturer has no control over actual application, no warranty is expressed or implied regarding the results to be obtained from the use thereof. User must determine suitability of this product for the intended application and assume all risk and liability in connection therewith.

FOR INDUSTRIAL USE ONLY: KEEP OUT OF REACH OF CHILDREN.

www.smooth-on.com