

# Guardian NC4™ Nitrile Examination Gloves

advetage  
solutions

In partnership with



The Guardian NC4™ powder-free, nitrile gloves offer consistent, dependable protection without sacrificing comfort or durability. These soft and stretchy 4 mil thick gloves are finger textured for enhanced grip and tactile sensitivity and tested for use with chemotherapy & cytotoxic drugs.

**Multi-Purpose:** The perfect choice for workers in healthcare, sciences, industrial or food handling industries.

## PRODUCT SPECIFICATIONS

- MEDICAL GRADE: CONFORMS TO ASTM D6319
- TESTED FOR USE WITH CHEMOTHERAPY DRUGS PER ASTM D6978
- FDA 510(K) REGISTRATION
- ENHANCED STRENGTH
- ACCELERATOR-FREE NITRILE
- FINGER TEXTURED SURFACE
- ANTI-SLIP GRIP
- AMBIDEXTROUS
- POWDER-FREE
- BEADED CUFF
- COLOR: SKY BLUE
- CHLORINATED
- MULTI-PURPOSE
- MANUFACTURED TO ISO 13485:2016

## PRICING GUIDE

	QUANTITY	PRICE
BOX	100 GLOVES	\$14.95
CASE*	1,000 GLOVES	\$149.50

**\*FREE 2-DAY SHIPPING**

## SCAN AND ORDER TODAY



**USE PROMO CODE "SAVE NOW" FOR AN ADDITIONAL 10% OFF YOUR FIRST ORDER**

**EMAIL US TO SIGN UP FOR AN ACCOUNT TO RECEIVE ADDITIONAL SAVINGS OR INQUIRE ABOUT BULK DISCOUNTS**

Phone: 424-292-8432

Email: SALES@ADVETAGE.COM

www.advetage.com/GUARDIAN

advetage  
solutions

# GuardianTouch NC4™ Nitrile Examination

## PHYSICAL DIMENSIONS

SIZE	Small	Medium	Large	X-Large	Inspection level/ AQL
Palm width (mm)	85 ± 5	95 ± 5	105 ± 5	115 ± 5	S2/AQL 4.0
Length (mm)	>240	>240	>240	>240	
Thickness at palm (center)	Typical Value 0.07 - 0.08 mm ( 2.8 - 3.1 mil )				
Thickness at finger from tip	Typical Value 0.11 - 0.13 mm ( 4.3 - 5.1 mil )				
Thickness at Cuff from cuff edge	Typical Value 0.06 - 0.07 mm ( 2.4 - 2.8 mil )				

## QUALITY & CONFORMITY

*\*The information on this document is a guideline of typical values and characteristics of the product\**

Manufactured under EN ISO 13485:2016, ISO 9001, and MDSAP Quality Management Systems

Conforms to

- ASTM D6319 and EN455
- Class 1 with approved 21CFR 820 FDA 510(K)

Conforms to the following additional test standards:

- ASTM D6978 Tested for use with Chemotherapy Drugs\*

Watertight Test	Inspection level /AQL
Freedom from Holes	GI/ AQL 1.5
Visual Inspection	Inspection level /AQL
Major Visual Defects	GI/ AQL 2.5

Tensile Strength (Mpa)	Minimm 14	Typical Value 26-30
Elongation:	Minimum 500%	Typical Value 560%-580%

- ASTM D412 Tensile Properties of Vulcanized Rubbers
- ASTM D3578 Standard Specification for Rubber Examination Gloves
- ASTM D5151-99 Standard Test for Detection of Holes in Medical Gloves
- ASTM D573 Accelerated Aging for Rubber:

### After Aging

Tensile Strength (Mpa)	Minimm 14	Typical Value 30-34
Elongation:	Minimum 400%	Typical Value 430%-450%

- ASTM D6124 Test Method for Residual Powder on Medical Gloves: <2.0 mg/glove

\*Cisplatin, Cyclophosphamide, Dacarbazine, Doxorubicin HCl, Etoposide, Fluorouracil, Methotrexate, Paclitaxel. <sup>1</sup> Gloves used for protection against chemotherapy drug exposure should be selected specifically for the type of chemicals used. Users should review the drug labeling or material safety data sheets for the chemicals being used to determine an adequate level of protection for the intended use.

## PRODUCT NUMBERS

SIZE	PRODUCT #	CASE QTY
SMALL	NC41CS1000	1000
MEDIUM	NC42CS1000	1000
LARGE	NC43CS1000	1000
X-LARGE	NC44CS1000	1000

## PACKAGING

100 gloves per box
10 boxes per case
1000 gloves per case



advetage  
solutions

111 Penn St. Suite 206  
El Segundo CA, 90245

Advantage Solutions and Apiary Medical are Service-Disable Veteran-Owned Small Businesses committed to supporting US Veterans. A portion of profits from the sale of Guardian™ NC4 Gloves go to non-profit organizations assisting Veterans in need.

Apiary  
MEDICAL